

Metallic Silver

General

It is a water based printing base used to achieve elastic and soft touching glitter silver effect in textile printing.

Advantages

- It provides easy use during print.
- It is advise to fix, the dry-wet rubbing and washing fastness are high.
- Suitable to ecological standards.

Applications

- It is used to achieve elastic and soft touching glitter silver effect in textile printing.
- Rubbing and washing tests should be applied 24 hours after used.
- Never use water to reduce the viscosity.
- Its curing time is at 160-170 °C; 1,5- 2 mins or 140 - 150 °C; 2 - 2,5 mins.

Usage

- It is advised to print with the silk-screen that are made between 34- 55 mesh.
- 50- 60 Shore, U type should be used.
- After using, the silk-screen should be cleaned with water.

Storage & Shelf Life

- Keep containers dry and tightly closed. Store in a ventilated place between (+5)-(+30)°C /(+41)-(+86)°F of temperature.
- It should be consumed within 2 years after the production date.



Technical Details



Appearance Paste



Odor

Characteristic



Color

Metallic-Silver



Viscosity

[(77 °F/25°C) sp: 6, rpm: 20 Brookfield]: 30.000-35.000 [mPa.s]



Density

1,05 g/cm3 (77 °F)



pН

7.5 – 8.0



Boiling Point

>100 °C (212 °F)



Solubility

Soluble in water



Explosion Hazard

It is not explosive



Packaging Information

Metallic Silver is packed in 1/5/10/20/30/60 kg plastic cans

Important

The technical application and information that have been given above, are designed only as using instructions. Should not be considered as a warranty for any other use. When any help or assistance is required, our technical department is ready for help.

In case of emergency, Safety Data Sheet of this product should be ready for help at the working area. The warnings are given on safety data sheet of this product is for use outside the manufacturer/ distributor to direct/indirect can not be held responsible for any loss or damage.

Rev. DATE: 1 December 2021

Rev. No: 03