

PF Poly White

General

It is a Phthalate Free printing base used to achieve an elastic, soft touching and white covering effect in textile printing.

Advantages

- PF Poly White provides for white covering alive effect and elastic.
- If used correctly as advised, It does not dry during the print and block in the silk-screen.
- It is phthalate free. However, it is not suitable to ecological standards because it contains PVC. It provides high efficiency on polyester fabrics

Applications

- PF Poly White is used for white covering alive effect on surface.
- Its curing time is at 302°F / 150°C; 1,5 mins.

Usage

- Fluorescent colors can be used to make alive colors,
- It can be mixed with PF pigments.
- It is advised to print with the silk-screens that are made between 34-62 mesh (80-160 inch). 60 – 80 Shore, V type dr. blade should be used.
- Before use, please stir this product well. Do not use any additives that are not advised.
- After using, the screen should be cleaned with the synthetic thinner.

Storage & Shelf Life

- Keep containers dry and tightly closed. Store in a ventilated place between (+5)-(+30)°C /(+41)-(+86)°F of temperature.
- It should be consumed within 2 years after the production date.

Technical Details



Appearance Paste



Odor Characteristic



Color White



Viscosity

[(25 °C) sp: 7, rpm: 2 Brookfield]: 1.200.000 - 1.600.000 [mPa.s]

TECHNICAL DATA SHEET



Density

1,461 g/cm³ (25°C)



pΗ



Boiling Point >100 °C (212 °F)



Solubility

Dispersible in water



回

Explosion Hazard It is not explosive



Packaging Information

PF Poly White is packed in 1/5/10/20/25/30/60 kg cans.

Important

The technical application and information that have been given above, are designed only as using instructions. Should not be considered as a warranty for any other use. When any help or assistance is required, our technical department is ready for help.

In case of emergency, Safety Data Sheet of this product should be ready for help at the working area. The warnings are given on safety data sheet of this product is for use outside the manufacturer/ distributor to direct/indirect can not be held responsible for any loss or damage.

Rev. DATE: August 2021 Rev. No: 03