

Reflective

General

It is a water based printing base used to achieve bright, elastic and soft touching reflective effect in textile printing.

Advantages

- It provides easy use during print.
- It is advise to fix, the dry-wet rubbing and washing fastness are high.
- Suitable to ecological standards.

Applications

- It is used to achieve elastic and soft touching reflective effect in textile printing.
- Rubbing and washing tests should be applied 24 hours after used.
- Never use water to reduce the viscosity.
- Its curing time is at 320°F / 160°C; 1,5 mins or 280°F / 140°C; 2 mins.

Usage

- Before usage, please stir the product well.
- Do not use any additives that are not advised.
- It is advised to print with the silk-screen that are made between 27-43 mesh.
- 50-70 Shore, U type should be used.
- After using, the silk-screen should be cleaned with water.

Storage & Shelf Life

- Keep containers dry and tightly closed. Store in a ventilated place between (+5)-(+30)°C /(+41)-(+86)°F of temperature.
- It should be consumed within 2 years after the production date.

Technical Details



Appearance Paste



Odor Characteristic



Color Reflective



Viscosity

30.000 - 50.000 mPA.s

TECHNICAL DATA SHEET



Relative Density 1,06 g/cm3 (77°F)

pH 7,5 - 8,0



Boiling Point >100°C (212°F)

၀၀္ဂံဝ

SolubilitySoluble in water



Explosion Hazard It is not explosive

回

Packaging InformationReflective is packed in 1/5/10/20/30/60 kg plastic cans.

Important

The technical application and information that have been given above, are designed only as using instructions. Should not be considered as a warranty for any other use. When any help or assistance is required, our technical department is ready for help.

In case of emergency, Safety Data Sheet of this product should be ready for help at the working area. The warnings are given on safety data sheet of this product is for use outside the manufacturer/ distributor to direct/indirect can not be held responsible for any loss or damage.

Rev. DATE: 1 December 2021 Rev. No: 02